

Document Name	Document No.	Ver	Date	Page
LP603048LC-PCM-LD Specification	ZJQM-RD-SPC-0647	0.0	2010/7/30	1/8

EEMB CO., LTD

Polymer Li-ion Battery Specification

Model: LP603048LC-PCM-LD

Capacity: 900mAh

Prepared	Checked	Approved

Customer:

Checked Approved	Signature	Oh a daa d	A

Address: Room ABCD,25/F, Block A, Fortune Plaza, NO.7060 Shennan Road Shenzhen, China

Postal code: 518040

Phone: 0086-755-83022275 FAX: 0086-755-83021966

http://www.eemb.com



Document Name	Document No.	Ver	Date	Page
LP603048LC-PCM-LD Specification	ZJQM-RD-SPC-0647	0.0	2010/7/30	2/8

Catalog

Chapter	Content	Page
0	Catalog	2
1	Scope	3
2	Product Basic Characteristics.	3
2.1	Model	3
2.2	Capacity	3
2.3	Nominal Voltage	3
2.4	Weight	3
2.5	Internal Impedance	3
2.6	Dimension	3
2.7	Charge.	3
2.8	Discharge	3
2.9	Operation Temperature.	3
2.10	Storage Temperature.	3
2.11	Storage Relative Humidity	3
3	Shape and Dimensions.	3
4	Appearance	3
5	Specification	4
5.1	Electrical Characteristics.	4
5.1.1	1C ₅ A rate discharge capacity.	4
5.1.2	High temp. discharge capacity	4
5.1.3	Low temp. discharge capacity	4
5.1.4	Cycle Life	4
5.1.5	Capacity Retention.	4
5.2	Acclimatization Characteristics.	4
5.2.1	High Temp. and High Humidity	4
5.2.2	Vibration	4
5.2.3	Drop.	4
5.3	Safety Characteristics.	5
5.3.1	Overcharge	5
5.3.2	Short-Circuit.	5
5.3.3	Heating	5
6	Spec of PCM.	5-6
7 8	Battery Pack's dimension	6 6
9	Warranty	6
10	Matters needing attention.	6-8



Document Name	Document No.	Ver	Date	Page
LP603048LC-PCM-LD Specification	ZJQM-RD-SPC-0647	0.0	2010/7/30	3/8

1. Scope


This product specification defines the requirements of the rechargeable polymer lithium-ion battery supplied to the customer by EEMB Co., Ltd..

2. Product Basic Characteristics

No.		Item	Characterist	ics	Remark
2.1		Model	LP603048L	С	
2.2	Capacity	Nominal Capacity	900	mAh	$0.2C_5A$
2,2	Сараспу	Minimum	850	mAh	$0.2C_5A$
2.3	Nom	inal Voltage	3.7	V	
2.4	Weight		Approx. 18	g	
2.5	Internal Impedance		≤ 100	$m\Omega$	AC 1KHz
		Length	≤ 49.0	mm	
2.6	Dimension	Width	≤ 30.5	mm	
		Thickness	≤ 6.3	mm	
		Maximum Current	900	mA	1.0C ₅ A (CC&CV)
2.7	Charge	Limited Voltage	4.200 ± 0.020	V	
		End-of Current	18	mA	
2.8	Discharge	Maximum Current	1800	mA	2.0C ₅ A
2.0	Discharge	End Voltage	2.750 ± 0.005	V	
2.9	Operation	Charge	0 ~ 45	$^{\circ}$	
2.7	Temperature	Discharge	-40 ∼ +60	$^{\circ}\!\mathbb{C}$	
	Storago	1 month	-20 ~ +60	$^{\circ}\!\mathbb{C}$	
2.10	Storage Temperature	3 month	-20 ∼ +45	$^{\circ}\!\mathbb{C}$	
	Temperature	12 month	-20 ~ +25	$^{\circ}$	
2.11	Storage R	elative Humidity	65±20	%	

3. Shape and Dimensions (Unit: mm)

Item	Specification
Т	Max6.3
W	Max30.5
L	Max49.0
L1	Max50.0
L2	10±1
M	16.0±1
N	3.0±0.5





Document Name	Document No.	Ver	Date	Page
LP603048LC-PCM-LD Specification	ZJQM-RD-SPC-0647	0.0	2010/7/30	4/8

4. Appearance

It shall be free from any defects such as remarkable scratches, breaks, cracks, discoloration, leakage, or middle deformation.

5. Specification

5.1 Electrical Characteristics

No.	Item	Criteria	Test Instructions
5.1.1	1C ₅ A rate discharge capacity	Discharge Time≥57min	Full charge at $20\pm5^{\circ}$ C, rest for 30 min, then discharge at the same temperature with $1.0C_5A$ to $2.75V$.
5.1.2	High temp. discharge capacity	Discharge Time≥54min	Full charge at $20\pm5^{\circ}$ C, store at $55\pm2^{\circ}$ C for 2h, then discharge at the same temperature with $1.0C_5A$ to $2.75V$.
5.1.3	Low temp. discharge capacity	Discharge Time≥2.5h	Full charge at 20 ± 5 °C, store at -40 °C ±2 °C for $16h\sim24h$, then discharge at the same temperature with $0.2C_5A$ to $2.75V$
5.1.4	Cycle Life	≥300Cycles	After full charge, rest for 10 min, discharge at constant current of 1.0C ₅ A to 2.75V. Batteries are full charge after 10 minutes. Repeat above steps till retained capacity is 80%
5.1.5	Capacity Retention	Discharge Time≥4.5 h	After full charge, store at 20 ± 5 °C for 28 days. Then discharge with $0.2C_5A$ to $2.75V$

5.2 Acclimatization Characteristics

No.	Item	Criteria	Test Instructions
5.2.1	High Temp. and High Humidity	no fire or explosion;	After full charge, store at $40^{\circ}\text{C} \pm 2^{\circ}\text{C} (90\% \sim 95\%\text{RH})$ for 48h. After test, place at $20^{\circ}\text{C} \pm 5^{\circ}\text{C}$ for 2h and then discharge with $1\text{C}_5\text{A}$ to end-voltage
5.2.2	Vibration	leakage, no smoking or explosion;	Batteries are vibrated 30 min in three mutually perpendicular directions with amplitude of 0.38mm (10~30Hz) or 0.19mm (30~55Hz) and the scanning rate of loct per min
5.2.3	Drop	or explosion;	Batteries are dropped onto a hard board with the thickness of $18\sim20$ mm from 1meter. Drop the batteries from six different directions and discharge them at $1C_5A$ to end of voltage.



Document Name	Document No.	Ver	Date	Page
LP603048LC-PCM-LD Specification	ZJQM-RD-SPC-0647	0.0	2010/7/30	5/8

5.3 Safety Characteristics

No.	Item	Criteria	Test Instructions
			Put the batteries with thermocouple into the
			ventilation cabinet. Connect the polarities to constant
5.3.1	Overcharge	No fire or explosion	voltage and adjust the current to 3C ₅ A, voltage to 4.8V.
			Charged the cells at 3C ₅ A current 20±5°C with a voltage
			limit of 4.8V and Current approach 0 A.
			Put the batteries with thermocouple into the ventilation
		No fire or explosion;	cabinet. Batteries are short-circuited by connecting the
5.3.2	Short-Circuit	The maximum Temperature:	positive and negative terminals for 1h with a resistance
		150℃	load of $100 \text{m}\Omega$. Test the temperature of the batteries
			until it drops to 10℃.
			Cell is heated in a circulating air oven at a rate of (5±2)
5.3.3	Heating	No fire or explosion	$^{\circ}$ C per minute to 130±2 $^{\circ}$ C, and then placed for 30
		-	minutes at 130±2°C
Note: I	Inless otherwise	specified all tests stated in this	specification are conducted at the following conditions:

Note: Unless otherwise specified, all tests stated in this specification are conducted at the following conditions: Temp. : $20\pm5^{\circ}$ C; Relative Humidity: $25\%\sim85\%$.

6. Specification of PCM

The specification shall be applied to Lithium polymer battery protection circuit module manufactured by EEMB CO., LTD.

6.1.0 Basic Specification(T=25°C)


Item	Symbol	Content	Criterion
	V _{DET1}	Over charge detection voltage	4.28±0.05V
Over charge Protection	tV _{DET1}	Over charge detection delay time	0.96S-1.40S
	V_{REL1}	Over charge release voltage	4.175±0.025V
	V _{DET2}	Over discharge detection voltage	2.30±0.10V
Over discharge protection	tV _{DET2}	Over discharge detection delay time	115ms-173ms
	V_{REL2}	Over discharge release voltage	2.40±0.050V
	V _{DET3}	Over current detection voltage	0.10±0.015V
0	I_{DP}	Over current detection current	2.0-6.0A
Over current protection	tV _{DET3}	Detection delay time	7.2ms-11.0ms
		Release condition	Cut load
		Detection condition	Exterior short circuit
Short protection		Release condition	Cut short circuit
Interior resistance	R _{DS}	Main loop electrify resistance	VC=4.2V,R _{DS} ≤70mΩ
Current consumption	I_{DD}	Current consume in normal operation	3μA Type 7μA Max

^{*}Note: These specs are guaranteed by design not by production tests.




Document Name	Document No.	Ver	Date	Page
LP603048LC-PCM-LD Specification	ZJQM-RD-SPC-0647	0.0	2010/7/30	6/8

6.2.0 PCM Circuit Diagram



7. Pack's Dimension



8. PACK 's voltage and internal resistance

Volatage: 3.7~3.9V

Internal Resistance: $\leq 200 \text{m} \Omega$

9. Warranty

One year warranty.

10. Matters needing attention

Strictly observes the following needing attention. EEMB will not be responsible for any accident occurred by handling outside of the precautions in this specification.



Document Name	Document No.	Ver	Date	Page
LP603048LC-PCM-LD Specification	ZJQM-RD-SPC-0647	0.0	2010/7/30	7/8

- Strictly prohibits heat or throw cell into fire.
- Strictly prohibits throw and wet cell in liquid such as water, gasoline or drink etc.
- Strictly prohibits use leave cell close to fire or inside of a car where temperature may be above 60°C. Also do not charge / discharge in such conditions.
- Strictly prohibits put batteries in your pockets or a bag together with metal objects such as necklaces. Hairpins, coins, or screws. Do not store or transportation batteries with such objects.
- Strictly prohibits short circuit the (+) and (-) terminals with other metals.
- Do not place Cell in a device with the (+) and (-) in the wrong way around.
- Strictly prohibits pierce Cell with a sharp object such as a needle.
- Strictly prohibits disassemble or modify the cell.
- Strictly prohibits welding a cell directly.
- Do not use a Cell with serious scar or deformation.
- Thoroughly read the user's manual before use, inaccurate handling of lithium ion rechargeable cell may cause leakage, heat, smoke, an explosion, or fire, capacity decreasing.

! Warning

- Strictly prohibits put cell into a microware oven, dryer, or high-pressure container.
- Strictly prohibits use cell with dry cells and other primary batteries, or new and old battery or batteries of a different package, type, or brand.
- Stop charging the Cell if charging is not completed within the specified time.
- Stop using the Cell if abnormal heat, odor, discoloration, deformation or abnormal condition is detected during use, charge, or storage.
- Keep away from fire immediately when leakage or foul odor is detected.
- If liquid leaks onto your skin or clothes, wash well with fresh water immediately.
- If liquid leaking from the Cell gets into your eyes, do not rub your eyes. Wash them well with clean edible oil and go to see a doctor immediately.

! Caution

- Before using the Cell, be sure to read the user's manual and cautions on handling thoroughly.
- Charging with specific charger according to product specification. Charge with CC/CV method.
 Strictly prohibits revered charging. Connect cell reverse will not charge the cell. At the same time, it will reduce the charge-discharge characteristics and safety characteristics, this will lead to product heat and leakage.
- Store batteries out of reach of children so that they are not accidentally swallowed.
- If younger children use the Cell, their guardians should explain the proper handling.
- Before using the Cell, be sure to read the user's manual and cautions on handling thoroughly.
- Batteries have life cycles. If the time that the Cell powers equipment becomes much shorter than usual, the Cell life is at an end. Replace the Cell with a new same one.
- When not using Cell for an extended period, remove it from the equipment and store in a place with low humidity and low temperature.
- While the Cell pack is charged, used and stored, keep it away from objects or materials with static electric charges.
- If the terminals of the Cell become dirty, wipe with a dry clothe before using the Cell.
- Storage the cells in storage temperature range as the specifications. After full discharged, we suggest that charging to 3.9~4.0V with no using for a long time.
- Do not exceed these ranges of the following temperature ranges:

Charge temperature range : 0° C to 45° C;



Document Name	Document No.	Ver	Date	Page
LP603048LC-PCM-LD Specification	ZJQM-RD-SPC-0647	0.0	2010/7/30	8/8

Discharge temperature range : -40° C to 60° C. Store less than 1 month : -20° C - $+60^{\circ}$ C Store less than 3 months : -20° C - $+45^{\circ}$ C Store less than 1 year : -20° C - $+25^{\circ}$ C

! Special Notice

Keep the cells in 50% charged state during long period storage. We recommend to charge the battery up to 50% of the total capacity every 3 months after receipt of the battery and maintain the voltage 3.7~4.1V. And store the battery in cool and dry place.