

# Lithium-ion Battery DATA SHEET

Battery Model: LIR14500

Prepared	Authorized	Approved
Jun,Wong	Wei , Lau	Ji de, Wong

Manufacturer: EEMB Co., Ltd. Website: http://eemb.com



Edition: DEC. 2006

This Specification describes the requirements of the lithium ion rechargeable battery supplied by EEMB Co., Ltd.

#### 1.0 BASIC CHARACTERISTICS

1.1	Battery Type	LIR14500	
1.2	Nominal Capacity	800mAh (0.2C discharge)	
Minimum Capacity		750mAh (0.2C discharge)	
1.3	Charging Voltage	4.2V	
1.4	Nominal Voltage	3.7V	
1.5	Standard Charge	Method: CC/CV (constant current / constant voltage) Current: 0.5C Voltage: 4.2V End Current:: 7mA	
1.6	Maximum Charge Current	800mA	
1.7	Maximum Discharge Current	1600mA	
1.8	End of Discharge Voltage	2.75V	
1.9	Weight	Approx. 20g	
1.10	Operating Temperature	Charge: 0 °C ~ 45°C Discharge: -20 °C ~ 60°C	
1.11	Storage Temperature	-5°C ~ 35°C	
1.12	Appearance	There shall be no such defect as scratch, flaw, crack, rust, leakage, which may adversely affect commercial value of the cell.	

#### 2.0 TECHNICAL REQUIREMENTS

## 2.1 Testing Conditions (unless otherwise specified)

Temperature: 20±5°C

Relative Humidity: 65±20%RH

Accuracy of voltmeters and ammeters used in the test is equal to or better than the

grade 0.5

## 2.2 Electrical Characteristics

NO	ITEM	TESTING INSTRUCTION	REQUIREMENTS
		Charge the battery with constant current 0.5C	
2.2.1	Charge	to 4.2V, and then charge at constant voltage	
2.2.1	Condition	4.2V until the current decays to 7mA during	
		the constant voltage stage.	





Li-ion Battery Edition: DEC. 2006


			Edition: DEC. 2006
2.2.2	Nominal Capacity	Within one hour after the charge according to 2.2.1, discharge at 0.2C until 2.75V cut-off voltage.	Capacity ≥ nominal capacity
2.2.3	1C discharge	With in 1 hours after the charge according to 2.2.1, discharge at constant current 1C until 2.75V cut-off voltage. If the discharge duration does not reach specified value, the test may be repeated up to three times in total.	≥ 95% of the nominal capacity
2 2 4	Internal	The initial internal resistance shall be	The initial internal
2.2.4	Resistance	measured at AC 1000Hz initially.	resistance≤80mohm
2.2.5	Cycle Life	After the charge according to 2.2.1, the battery stays for 1 hour.  At 25±5°C, discharge the battery at constant current 0.5C until 2.75V cut-off voltage. Then the battery stays for 1 hour. A cycle defined as one charge and discharge. This charge and discharge circle shall be repeated 300 times.	The capacity at 300th cycle ≥ 80% of the nominal capacity
2.2.6	Electricity Preservation	After the charge according to 2.2.1, the battery stays at 20±5°C for 28 days and then discharge at 0.2C to 2.75V cut-off.	The discharge capacity 80% of the nominal capacity
0.07	High Temperature Performance	After the charge according to 2.2.1, store the testing cells at 60±2°C for 4 hours. Then discharge at 1C until 2.75V cut-off voltage.	The discharge capacity 90% of the nominal capacity
2.2.7	Low Temperature Performance	After the charge according to 2.2.1, store the testing cells at -20±2°C for 4 hours. Then discharge at 0.2C until 2.75V cut-off voltage	The discharge capacity 60% of the nominal capacity
2.2.8	Short-circuit	After the charge at 2.2.1, short circuit the cathode and anode. Stop testing when battery temperature decays to about 10°C from the maximum temperature.	No fire, no explosion
2.2.9	Overcharge	Put the testing batteries connecting with thermocouple in ventilated cabinet, connect the cathode and anode to a power supply with CC/CV (constant current / constant voltage) function. Adjust the current to 3C and voltage to 4.6V. Then charge the battery at 3C until the limit voltage reaches 4.6V. The charging continued for 8 hours.	No fire, no explosion



Li-ion Battery Edition: DEC. 2006


2.2.10	Hot box test	Put the testing batteries connecting with thermocouple in constant temperature box. Heat the batteries and box (speed of ascending temperature is 5±2°C at room temperature simultaneously). Monitor the temperature change of the box. Keep for 10 minutes after the box temperature reaches 150±2°C, then stop the test.	No fire, no explosion
2.2.11	Vibration test	After the charge at 2.2.2, put the testing battery on the vibration testing equipment. Vibrate it from X,Y two different directions for 30 minutes (Frequency of vibration: 10Hz-30Hz, displacement of single swing: 0.38mm; Frequency of vibration: 30Hz-55Hz, displace of single swing: 0.19mm) in swept vibration from 10Hz to 50Hz. The swept rate is 1 oct/min.	No fire, no explosion  ≥ 90% of the nominal capacity
2.2.12	Drop test	After the charge at 2.2.2, free drop the testing battery from the height of 1.0 meter (the lowest point height) once from the each six positive and negative X,Y,Z directions to the hardwood board (the thickness of the board is about 50mm).	No fire, no explosion ≥ 90% of the nominal capacity


# 3.0 BATTERY DIMENSION






#### 4.0 DISCHARGE CHARACTERITICS.







#### 5.0 Protection

When Li-ion rechargeable battery is used over the permitted voltage or current, electrolyte may disassemble, and this case will affect safety performance of Li-ion rechargeable battery. So protection circuit module were used in order to prevent overcharge, over discharge and over current.

The parameters of protection circuit module as follows:

Overcharge Protection Voltage :  $4.25V \pm 25mV$ Overdischarge Protection Voltage :  $2.30V \pm 80mV$ 

Overcurrent Protection Voltage: ≤3.0 A

Li-ion Battery Edition: DEC. 2006

#### 6.0 WARNINGS AND CAUTIONS IN HANDLING THE Lithium-ion BATTERY

To prevent a possibility of the battery from leaking, heating or explosion please observe the following precautions:

#### **WARNINGS!**

- 1) Do not immerse the battery in water or seawater, and keep the battery in a cool dry surrounding if it stands by.
- 2) Do not use or leave the battery near a heat source as fire or heater
- 3) When recharging, use the battery charger specifically for that purpose
- 4) Do not reverse the position (+) and negative (-) terminals
- 5) Do not connect the battery to an electrical outlet
- 6) Do not discard the battery in fire or heat it
- 7) Do not short-circuit the battery by directly connecting the positive (+) and negative (-) terminal with metal objects such as wire.
- 8) Do not transport or store the battery together with metal objects such as necklaces, hairpins etc.
- 9) Do not strike or throw the battery
- 10) Do not directly solder the battery and pierce the battery with a nail or other sharp object.

#### **CAUTIONS!**

- 1) Do not use or leave the battery at very high temperature (for example, at strong direct sunlight or in a vehicle in extremely hot weather). Otherwise, it can overheat or fire or its performance will be degenerate and its service life will be decreased.
- 2) Do not use it in a location where static electricity is great, otherwise, the safety devices may be damaged, causing hidden trouble of safety.
- 3) If the battery leaks, and the electrolyte get into the eyes. Do not rub eyes, instead, rinse the eyes with clean running water, and immediately seek medical attention. Otherwise, it may injure eyes or cause a loss of sight.
- 4) If the battery gives off an odor, generates heat, becomes discolored or deformed, or in any way appear abnormal during use, recharging or storage, immediately remove it from the device or battery charger and stop using it.
- 5) In case the battery terminals are dirt, clean the terminals with a dry cloth before use. Otherwise power failure or charge failure may occur due to the poor connection with the instrument.
- 6) Be aware discarded batteries may cause fire, tape the battery terminals to insulate them.

#### Special notice!

Keep the cells in 50% charged state during long period storage. We recommend to charge the battery up to 50% of the total capacity every 3 months after receipt of the battery and maintain the voltage 3.7~4.1V. And store the battery in cool and dry place.

Note: Any representations in this brochure concerning performance, are for informational purposes only and are not construed as warranties either expressed or implied, of future performance.